

Alleima® 3R64 is an austenitic stainless steel with a high molybdenum content. Significant properties, such as general and pitting corrosion resistance, are improved, in comparison with ASTM 316L.

sentence correction

Standards

- ASTM: 317L
- UNS: S31703
- EN Number: 1.4438
- W.Nr.: 1.4438
- SS: 2367
- BS: 317S16

Product standards

- EN 10088-3
- ASTM A-314

Suitable for production of flanges etc. according to ASTM A-182

Certificates

Status according to EN 10 204 3.1

Chemical composition (nominal) %

C	Si	Mn	P	S	Cr	Ni	Mo	Others
≤0.030	0.4	1.8	≤0.030	≤0.010	18.5	14.5	3.1	-

Forms of supply

Sizes and tolerances

Round-cornered square, as well as round billets, are produced in a wide range of sizes according to the following tables. Larger sizes offered on request.

Surface conditions

Square billets

Unground, spot ground or fully ground condition.

Round billets

Peel turned or black condition.

Square billets

Size	Tolerance	Length
mm	mm	m
80	+/-2	4 - 6.3
100, 114, 126, 140, 150	+/-3	4 - 6.3
160, 180, 195, 200	+/-4	4 - 6.3
>200 - 350	+/-5	3 - 5.3

Sizes and tolerances apply to the rolled/forged condition.

Peel turned round billets

Size	Tolerance	Length
mm	mm	m
75 - 200 (5 mm interval)	+/-1	max 10
>200 - 450	+/-3	3 - 8

Unground round billets

Size	Tolerance	Length
mm	mm	m
77 - 112 (5 mm interval)	+/-2	max 10
124, 134	+/-2	max 10
127, 147, 157	+/-2	max 10
142, 152, 163	+/-2	max 10
168, 178, 188	+/-2	max 10
183, 193	+/-2	max 10

Other products

- Hollow bar

Mechanical properties

At 20°C (68°F)

Metric units

Proof strength		Tensile strength	Elong.	Hardness
$R_{p0.2}^a$	$R_{p1.0}^a$	R_m	A^b	Vickers
MPa	MPa	MPa	%	
				approx.
≥220	≥250	515-690	≥35	155

Imperial units

Proof strength		Tensile strength	Elong.	Hardness
$R_{p0.2}^a$	$R_{p1.0}^a$	R_m	A^b	Vickers
MPa	MPa	MPa	%	
				approx.
≥32	≥36	75-100	≥35	155

1 MPa = 1 N/mm²

a) $R_{p0.2}$ and $R_{p1.0}$ correspond to 0.2% offset and 1.0% offset yield strength, respectively.

b) Based on $L_0 = 5.65 \sqrt{S_0}$ where L_0 is the original gauge length and S_0 the original cross-section area.

Impact strength

Due to its austenitic microstructure, Alleima® 3R64 has very good impact strength both at room temperature and at cryogenic temperatures.

Tests have demonstrated that the steel fulfils the requirements according to the European standards prEN 13445-2 (UFPV-2) (min. 60 J (44 ft-lb) at -270 °C (-455 °F)) and prEN 10216-5 (min. 60 J (44 ft-lb) at -196 °C (-320°F)).

At high temperatures

Metric units

Temperature	
Proof strength	
R	
$p0.2$	
a	
R	
$p1.0$	
a	

°C
MPa
MPa
min.
min.
50
196
221
100
172
197
150
155
180
200
144
169
250
136
161
300
129
154
350
123
148
400
119
144
450
115

140

500

110

135

Imperial units

Temperature

Proof strength

R

p0.2

a

R

p1.0

a

°F

MPa

ksi

min.

min.

200

25.4

29.0

400

20.8

24.4

600

18.4

22.1

800

17.0

20.6

1000

15.4

19.0

Disclaimer:

Recommendations are for guidance only, and the suitability of a material for a specific application can be confirmed only when we know the actual service conditions. Continuous development may necessitate changes in technical data without notice. This datasheet is only valid for Alleima materials.